

Technical Data Sheet

Softflex 0350

Thermoplastic Elastomer
LyondellBasell Industries
Engineering Plastics

Product Description

Softflex 0350 is suitable for overmolding polypropylene and polyethylene.

General


Agency Ratings	• EC 1907/2006 (REACH)	• EU 2002/96/EC (WEEE)
RoHS Compliance	• RoHS Compliant	
Forms	• Pellets	
Processing Method	• Coating	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.910	0.908 g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (235°C/1.0 Kg)	46 g/10 min	46 g/10 min	ASTM D1238
Elastomers	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	580 psi	4.00 MPa	ASTM D412
Tensile Elongation (Break)	950 %	950 %	ASTM D412
Tear Strength	130 lbf/in	22.8 kN/m	ASTM D624
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Gardner Impact (-22°F (-30°C))	320 in·lb	36.2 J	ASTM D5420
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness			ASTM D2240
Shore A	36 to 42	36 to 42	
Shore A, 10 Sec	32 to 38	32 to 38	

Technical Data Sheet

Softflex 0350

Thermoplastic Elastomer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Rear Temperature	290 to 310 °F	143 to 154 °C
Middle Temperature	315 to 335 °F	157 to 168 °C
Front Temperature	340 to 350 °F	171 to 177 °C
Nozzle Temperature	355 to 365 °F	179 to 185 °C
Mold Temperature	60 to 75 °F	16 to 24 °C
Injection Rate	Moderate-Fast	Moderate-Fast
Back Pressure	90.0 to 175 psi	0.621 to 1.21 MPa
Screw L/D Ratio	20.0:1.0	20.0:1.0
Screw Compression Ratio	1.5:1.0	1.5:1.0

Notes

These are typical property values not to be construed as specification limits.