



# Adsyl 5 C 30 F

## **Advanced Polyolefin**

#### **Product Description**

Adsyl 5 C 30 F is an advanced polyolefin, specially designed for use as a sealing or metallized layer in co-extruded film applications.

This grade features a very low seal initiation temperature and good optics.

It does not contain slip or anti-block additives.

For regulatory compliance information see the *Adsyl* 5 C 30 F Regulatory Affairs Product Stewardship Information/Certification Data Sheet (RAPIDS), which can be found on www.polymers.lyondellbasell.com.

#### **Product Characteristics**

Status Commercial: Active

Test Method used ISO ASTM

Availability Europe, North America, Asia-Pacific, Australia/NZ, Africa-

Middle East, Latin America

Processing Method Double Bubble, Cast Film, BOPP

Features Low Temperature Heat Sealability

**Typical Customer Applications** Stationery Film, Food Packaging Film, Lamination Film,

Double Bubble Shrink Film, Breathable Film

Typical Properties	Method	Value Unit
Physical		
Density -Specific Gravity	ASTM D 792	0.902 sp gr <b>23/23°C</b>
Melt flow rate (230°C/2.16kg)	ASTM D 1238	5.50 g/10 min
Mechanical		
Tensile Strength @ Yield	ASTM D 638	21.4 MPa
Flexural Modulus (1 mm/min, 1% Secant, Procedure A)	ASTM D 790	648 MPa
Tensile Elongation @ Yld	ASTM D 638	13 %
Impact		
Notched izod impact (23 °C, Method A)	ASTM D 256	85.4 J/m
Thermal		
DTUL @66psi - Unannealed	ASTM D 648	62.8 °C

#### **Additional Properties**

Film properties obtained on cast film produced with laboratory line under internal standard conditions.

Tensile Young modulus, MD/TD, ISO 527-3, 25 mm/min, 50  $\mu$ m: 280/280 MPa Stress at Yield, MD/TD, ISO 527-3, 500 mm/min, 50  $\mu$ m: 14/14 MPa Elongation at Yield, MD/TD, ISO 527-3, 500 mm/min, 50  $\mu$ m: 17/15 % Stress at Break, MD/TD, ISO 527-3, 500 mm/min, 50  $\mu$ m: 45/35 MPa Elongation at Break, MD/TD, ISO 527-3, 500 mm/min, 50  $\mu$ m: 900/800 %

### Notes

Typical properties; not to be construed as specifications.