

Adsyl 6 C 30 F

Advanced Polyolefin

Product Description

Adsyl 6 C 30 F is a new advanced polyolefin, specially designed for use as a sealing layer in coextruded film applications.

This grade features a very low seal initiation temperature (<100°C) and excellent optical properties.

It does not contain slip or anti-block additives.

For regulatory information please refer to Adsyl 6 C 30 F Product Stewardship Bulletin (PSB).

Product Characteristics

Status Commercial: Active

Test Method used ISC

Availability Europe, North America, Asia-Pacific, Australia/NZ, Africa-

Middle East, Latin America

Processing Methods BOPP, Cast Film, Double Bubble

Features Low Temperature Heat Sealability

Typical Customer ApplicationsDouble Bubble Shrink Film, Food Packaging Film, Lamination Film, Shrink Film, Stationery Film

Typical Properties	Method	Value	Unit
Physical			
Density (Method A)	ISO 1183	0.90	g/cm³
Melt flow rate (MFR) (230°C/2.16Kg)	ISO 1133	5.5	g/10 min
Thermal			
Melting temperature		128	°C
Note: ISO 11357-3			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	59	°C
Vicat softening temperature A/50	ISO 306	103	°C
Optical			
Haze (50 μm)	ASTM D 1003	0.2	%
Gloss (45°, 50 μm)	ASTM D 2457	92	
Film			
Seal initiation temperature		95	°C
Note: Internal test method			

Additional Properties

 $\label{lem:properties} Film\ properties\ obtained\ on\ cast\ film\ produced\ with\ laboratory\ line\ under\ internal\ standard\ conditions.$

Tensile Young modulus, MD/TD, ISO 527-3, 25 mm/min, 50 μ m: 260/250 MPa Stress at Yield, MD/TD,ISO 527-3, 500 mm/min, 50 μ m: 14/14 MPa Elongation at Yield, MD/TD, ISO 527-3, 500 mm/min, 50 μ m: 16/14 % Stress at Break, MD/TD,ISO 527-3, 500 mm/min, 50 μ m: 37/41 MPa Elongation at Break, MD/TD,ISO 527-3, 500 mm/min, 50 μ m: 850/900 %

Notes

Typical properties; not to be construed as specifications.