(+) 188 1699 6168 hongrunplastics.com



# **Dexflex 1066-UV**

## **Compounded Polyolefin**

## **Product Description**

 ${\it Dexflex}~1066\hbox{-}{\it UV}~is~a~thermoplastic~olefinic~elastomer~(TPO)~designed~for~automotive~exterior~applications~that~require~durable~paintability~in~large~injection~molded~parts.$ 

### **Product Characteristics**

**Status** Commercial: Restricted

Test Method used ISO

Availability North America

Processing Methods Injection Molding

**Features** Paintable, Low Temperature Toughness

**Typical Customer Applications** Exterior Applications

Method	Value	Unit
ISO 1183	0.89	g/cm³
ISO 1133	7.0	g/10 min
ASTM D 624	560	ppi
ISO 527-1, -2	20	MPa
ISO 178	600	MPa
ISO 868/ASTM D 2240	57	
ISO 294-4		
e recommendations.		
	ISO 1183 ISO 1133  ASTM D 624 ISO 527-1, -2 ISO 178  ISO 868/ASTM D 2240  ISO 294-4	ISO 1183 0.89 ISO 1133 7.0  ASTM D 624 560 ISO 527-1, -2 20 ISO 178 600  ISO 868/ASTM 57 D 2240

### Notes

Typical properties; not to be construed as specifications.