(+) 188 1699 6168 hongrunplastics.com

Technical Data Sheet

Hifax CA 7201 A

Catalloy



Product Description

Hifax CA 7201 A is a reactor TPO (thermoplastic polyolefin) manufactured using the LyondellBasell's proprietary *Catalloy* process technology.

It is primarily used for bumper and interior/exterior trim applications in Automotive. It has a very high impact performance, reduced shrinkage and a very good paintability. The material also has a high level of processability. The grade is available in natural pellet form.

Regulatory Status

For regulatory compliance information, see *Hifax* CA 7201 A <u>Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS)</u>.

Status Commercial: Active

Availability Africa-Middle East; Asia-Pacific; Australia and New Zealand; Europe; North America;

South & Central America

Application Bumpers; Exterior Automotive Applications; Exterior Trim; Interior Automotive

Applications; Polymer Modifier

Market Automotive; Compounding

Processing Method Compounding; Injection Molding

Attribute Good Adhesion; Good Dimensional Stability; Good Processability; Good Stiffness;

High Impact Resistance; Paintable

| lominal |
|---------|
| |

| Typical Properties | Value | Units | Test Method |
|---|-------|----------|---------------|
| Physical | | | |
| Melt Flow Rate, (230 °C/2.16 kg) | 11 | g/10 min | ISO 1133-1 |
| Density | 0.89 | g/cm³ | ISO 1183-1 |
| Mechanical | | | |
| Flexural Modulus | 750 | MPa | ISO 178 |
| Tensile Stress at Break | 16 | MPa | ISO 527-1, -2 |
| Tensile Stress at Yield | 17 | MPa | ASTM D638 |
| Tensile Strain at Break | >500 | % | ISO 527-1, -2 |
| Tensile Strain at Yield | 13 | % | ISO 527-1, -2 |
| Impact | | | |
| Charpy Impact Strength - Notched | | | |
| (23 °C) | 50 | kJ/m² | ISO 179 |
| (-20 °C) | 45 | kJ/m² | ISO 179 |
| (-40 °C) | 10 | kJ/m² | ISO 179 |
| Multi-axial Impact Strength, (-30 °C, 2.2 m/s, 3.2 mm plaque) | 23.9 | J | ASTM D3763 |
| Thermal | | | |
| Heat Deflection Temperature B, (0.45 MPa, Unannealed) | 65 | °C | ISO 75B-1, -2 |
| DSC Melting Point | 163 | °C | ISO 11357-3 |