(+) 188 1699 6168 hongrunplastics.com



# Hifax CA 7320 A

## **Advanced Polyolefin**

#### **Product Description**

Hifax CA 7320 A is a reactor TPO (thermoplastic polyolefin) manufactured using the LyondellBasell' s proprietary Catalloy process technology.

It is designed for use in compounds where it shows high efficiency as impact modifier. It gives excellent processability whilst maintaining optimum mechanical properties.

The grade is available in natural pellet form.

For regulatory compliance information see *Hifax* CA 7320 A Regulatory Affairs Product Stewardship Information/Certification Data Sheet (RAPIDS), which can be found on www.polymers.lyondellbasell.com.

# **Product Characteristics**

Status Commercial: Active

Test Method used ISO

Availability Europe, North America, Asia-Pacific, Australia/NZ, Africa-

Middle East, Latin America

Processing Methods Extrusion Compounding, Injection Molding

Features High Impact Resistance , Low Temperature Impact

Resistance, Good Moldability, Good Processability

**Typical Customer Applications** Exterior Applications, Impact modification

Typical Properties	Method	Value	Unit
Physical			
Density (Method A)	ISO 1183	0.88	g/cm³
Melt flow rate (MFR) (230°C/2.16Kg)	ISO 1133	2.5	g/10 min
Mechanical			
Tensile Stress at Break	ISO 527-1, -2	10	MPa
Tensile Strain at Break	ISO 527-1, -2	500	%
Flexural modulus	ISO 178	200	MPa
Impact			
Notched izod impact strength (-50 °C, Type 1, Notch A)	ISO 180	No Break	
Hardness			
Shore hardness (Shore D)	ISO 868	32	
Thermal			
Vicat softening temperature (A50 (50°C/h 10N))	ISO 306	60	°C
Melting temperature	DSC	162	°C
Note: ISO 11357-3			

## Notes

Typical properties; not to be construed as specifications.