

# Hifax CA 7378 A

## **Advanced Polyolefin**

#### **Product Description**

Hifax CA 7378 A is a reactor TPO (thermoplastic polyolefin) manufactured using the LyondellBasell's proprietary Catalloy process technology.

It is suitable for injection molding controlled shrinkage applications (e.g. automotive exterior or interior).

Hifax CA 7378 A exhibits high melt flow rate with good impact/stiffness balance and reduced shrinkage.

The grade is available in natural pellet form.

For regulatory compliance information see *Hifax* CA 7378 A Regulatory Affairs Product Stewardship Information/Certification Data Sheet (RAPIDS), which can be found on www.polymers.lyondellbasell.com.

### **Product Characteristics**

**Status** Commercial: Active

Test Method used ISO

**Availability** Europe, North America, Asia-Pacific, Australia/NZ, Africa-

Middle East, Latin America

**Processing Methods** Extrusion Compounding, Injection Molding

Features High Flow , Good Impact Resistance , Good Stiffness

**Typical Customer Applications** Automotive Parts, Exterior Applications, Polymer

modifier

Typical Properties	Method	Value	Unit
Physical			
Density (Method A)	ISO 1183	0.90	g/cm³
Melt flow rate (MFR) (230°C/2.16Kg)	ISO 1133	13	g/10 min
Mechanical			
Tensile Stress at Yield	ISO 527-1, -2	21	MPa
Tensile Strain at Break	ISO 527-1, -2	> 500	%
Tensile Strain at Yield	ISO 527-1, -2	8	%
Flexural modulus	ISO 178	1200	MPa
Impact			
Notched izod impact strength	ISO 180		
(23 °C)		37	kJ/m²
(-40)		5,5	kJ/m²
Thermal			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	90	°C
CLTE, Flow (23°C to 80°C)	ISO 11359-1, - 2	10 x 10E-5	cm/cm/°C

### **Additional Properties**

Shrinkage (internal test method): MD 0.9% TD 1.0%

### Note

Typical properties; not to be construed as specifications.