(+) 188 1699 6168 hongrunplastics.com



Hifax CB 1160 G1

Compounded Polyolefin

Product Description

Hifax CB 1160 G1 is a talc filled PP copolymer, with medium flowability, high impact resistance and good stiffness. This grade is delivered in customer customized colors. This Data Sheet is giving general properties, some of them may be slightly altered upon color selected.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Product Characteristics

Status	Commercial	
Availability	Europe	(1)
Processing Method	Injection molding	
Features	Surface appearance, impact resistance, stiffness, scratch resistance and UV resistance.	
Typical Customer Applications	Used for automotive unpainted bumper, as well as painted bump automotive exterior trims.	er and

Value **Typical Properties** Method Unit **Physical** Melt Flow Rate (230 °C, 2.16 kg) ISO 1133 14 g/10 min q/cm³ Density (23 °C) ISO 1183-1/A 0.97 Mechanical ISO 527-1, -2 Tensile Stress at Yield (23 °C) 18 MPa Flexural Modulus (23 °C) Tech. A ISO 178/A1 1400 MPa Flexural Strength (23 °C) Tech. A ISO 178/A1 MPa 22 **Impact** kJ/m² Izod Impact strength, notched (23 °C) 45 ISO 180/1A Izod Impact Strength, notched (-30 °C) kJ/m² ISO 180/1A 6.5 Thermal °C Vicat Softening Temperature B (50 N) **ISO 306** 52 °C Heat Deflection Temperature A (1.8 MPa) ISO 75-1, -2 50

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- · Keep material completely dry for good processing.

Notes

Typical properties; not to be construed as specifications.

(1): Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.