(+) 188 1699 6168 hongrunplastics.com



Hifax HKC 426P BLACK

Compounded Polyolefin

Product Description

Hifax HKC 426P BLACK is a 22% talc filled PP homopolymer, with high stiffness and high UV resistance. Product is available in black color, pellet form.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Product Characteristics

Status Commercial

Availability Europe (1)

Processing Method Injection molding

Features Stiffness, UV resistance.

Typical Customer Applications Used for automotive exterior trims.

| Typical Properties | Method | Value | Unit |
|--|---------------|-------|-------------------|
| Physical | | | |
| Melt Flow Rate (230 °C, 2.16 kg) | ISO 1133 | 11 | g/10 min |
| Density (23 °C) | ISO 1183-1/A | 1.04 | g/cm ³ |
| Mechanical | | | |
| Tensile Stress at Yield (23 °C) | ISO 527-1, -2 | 32 | MPa |
| Tens.Strain at Break | ISO 527-1, -2 | 15 | % |
| Flexural Modulus (23 °C) Tech. A | ISO 178/A1 | 2800 | MPa |
| Impact | | | |
| Charpy Impact Strength, notched (23 °C) | ISO 179-1/1eA | 3 | kJ/m ² |
| Charpy Impact Strength, notched (-30 °C) | ISO 179-1/1eA | 1.5 | kJ/m ² |
| Thermal | | | |
| Vicat Softening Temperature A (10 N) | ISO 306 | 150 | °C |
| Heat Deflection Temperature B (0.45 MPa) | ISO 75-1, -2 | 110 | °C |

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

Notes

Typical properties; not to be construed as specifications.

(1): Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.