



Hifax TRC 134P C11306

Compounded Polyolefin

Product Description

Hifax TRC 134P C11306 is a 20% talc filled PP copolymer, with very low shrinkage, good impact resistance and high UV resistance. Product is available as a customized color matched, pellet form. This grade is delivered in C11306 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Product Characteristics

Status	Commercial	
Availability	Europe	(1)
Processing Method	Injection molding	
Features	Shrinkage, impact resistance, UV resistance.	
Typical Customer Applications	Used for automotive partially painted bumper.	

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	20	g/10 min
Density (23 °C)	ISO 1183-1/A	1.05	g/cm ³
Mechanical			
Tens.Strain at Break	ISO 527-1, -2	500	%
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1400	MPa
Impact			
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	61	kJ/m ²
Charpy Impact Strength, notched (-30 °C)	ISO 179-1/1eA	7	kJ/m ²

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

Notes

Typical properties; not to be construed as specifications.

(1) : Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.