(+) 188 1699 6168 hongrunplastics.com



# Hifax TRC 221P G12808

# Compounded Polyolefin

## **Product Description**

Hifax TRC 221P G12808 is a 20% talc filled PP copolymer, with high flowability, excellent impact/stiffness balance and very low CLTE. Product is available as a customized color matched, pellet form. This grade is delivered in G12808 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

#### **Product Characteristics**

**Status** Commercial (1) Europe **Availability** Injection molding **Processing Method** Impact/stiffness balance, CLTE (Coefficient of Linear Thermal **Features** Expansion). **Typical Customer Applications** Used for applications demanding high impact strength as well as good

stiffness.

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	15	g/10 min
Density (23 °C)	ISO 1183-1/A	1.04	g/cm <sup>3</sup>
Mechanical			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	16.5	MPa
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1500	MPa
Impact			
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	55	kJ/m <sup>2</sup>
Charpy Impact Strength, notched (-40 °C)	ISO 179-1/1eA	3.5	kJ/m <sup>2</sup>
Izod Impact strength, notched (23 °C)	ISO 180/1A	48	kJ/m <sup>2</sup>
Izod Impact strength, notched (-40 °C)	ISO 180/1A	5	kJ/m <sup>2</sup>
Thermal			
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	95	°C

# **Product Storage and Handling**

- · Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- · Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- · Keep material completely dry for good processing.

### **Notes**

Typical properties; not to be construed as specifications.

(1): Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.