



Hifax TRC 277P S81533

Compounded Polyolefin

Product Description

Hifax TRC 277P S81533 is a 15% talc filled PP copolymer, with high melt flow rate, good impact/stiffness balance, improved surface appearance and excellent UV resistance. Formula is improved to offer better aspect, especially on tiger stripes. This material has been coloured to create a metallic effect.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Product Characteristics

Status	Commercial	
Availability	Europe	(1)
Processing Method	Injection molding	
Features	High melt flow rate, impact/stiffness balance, surface appearance, UV resistance.	
Typical Customer Applications	Used for applications that require excellent aesthetics and molded-in color applications and for automotive exterior trims.	

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	20	g/10 min
Density (23 °C)	ISO 1183-1/A	1.01	g/cm ³
Mechanical			
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1700	MPa
Impact			
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	20	kJ/m ²
Thermal			
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	95	°C

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

Notes

Typical properties; not to be construed as specifications.

(1) : Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.