



Hifax TRC 432X BLACK

Compounded Polyolefin

Product Description

Hifax TRC 432X BLACK is a 20% talc filled PP copolymer, with high flowability and good impact/stiffness balance. The product is available in black color, pellet form.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Product Characteristics

Status	Commercial	
Availability	Europe	(1)
Processing Method	Injection molding	
Features	Flowability, impact/stiffness balance.	
Typical Customer Applications	Used for automotive moulded, painted parts.	

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	22	g/10 min
Density (23 °C)	ISO 1183-1/A	1.06	g/cm ³
Mechanical			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	21	MPa
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	2400	MPa
Flexural Strength (23 °C) Tech. A	ISO 178/A1	32	MPa
Impact			
Izod Impact strength, notched (23 °C)	ISO 180/1A	12	kJ/m ²
Izod Impact Strength, notched (-30 °C)	ISO 180/1A	3.5	kJ/m ²
Thermal			
Vicat Softening Temperature B (50 N)	ISO 306	60	°C
Heat Deflection Temperature A (1.8 MPa)	ISO 75-1, -2	55	°C

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

Notes

Typical properties; not to be construed as specifications.

(1) : Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.