



## Hifax TRC 495P G13076

### Compounded Polyolefin

#### Product Description

Hifax TRC 495P G13076 is a 16% talc filled PP copolymer, with superior impact/stiffness balance, excellent flowability, good processability and good UV resistance. The product is also available as a customized color matched, pellet form. This grade is delivered in G13076 color version.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

#### Product Characteristics

Status	Commercial	
Availability	Europe	(1)
Processing Method	Injection molding	
Features	Superior impact/stiffness balance, good UV resistance, good processability.	
Typical Customer Applications	Used for outdoor/exterior applications.	

Typical Properties	Method	Value	Unit
<b>Physical</b>			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	20	g/10 min
Density (23 °C)	ISO 1183-1/A	1.0	g/cm <sup>3</sup>
<b>Mechanical</b>			
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1700	MPa

#### Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

#### Notes

Typical properties; not to be construed as specifications.

(1) : Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.