



Hifax TRC 779P

Compounded Polyolefin

Product Description

Hifax TRC 779P high melt flow, 1,650 MPa flexural modulus, UV-stabilized, paintable, mineral-filled thermoplastic elastomeric olefin (TEO) resin has an excellent balance of properties and processability. It was designed for use in multiple automotive exterior applications.

Product Characteristics

Status	Commercial: Active
Test Method used	ISO
Availability	North America
Processing Methods	Injection Molding
Features	Good Dimensional Stability, Good Flow, Good Impact Resistance , Low Temperature Impact Resistance, Good Moldability , Paintable, Low Shrinkage, High Stiffness, Good Weather Resistance
Typical Customer Applications	Bumpers, Exterior Applications

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230°C/2.16kg)	ASTM D 1238	25	g/10 min
Density (Method A)	ISO 1183	1.03	g/cm³
Mechanical			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	16	MPa
Tensile Strain at Yield (23 °C)	ISO 527-1, -2	4	%
Flexural modulus (23 °C)	ISO 178	1650	MPa
Impact			
Notched izod impact strength (-30 °C) (23 °C)	ISO 180		
		5.5	kJ/m²
		45	kJ/m²
Additional Information			
Mold shrinkage	ISO 294-4		
Note: Please contact Basell for shrinkage recommendations.			

Additional Properties

Multi-axial instrumented impact, energy at max load at -40°C (2.2 m/sec) = 23 J (ductile failure mode).

Notes

Typical properties; not to be construed as specifications.