(+) 188 1699 6168 hongrunplastics.com



# **Hifax TYC 1123P E C11538**

## **Compounded Polyolefin**

## **Product Description**

Hifax TYC 1123P E is a 17% talc filled PP copolymer, with high melt flow rate, low density and very good surface appearance. This grade is delivered in customer customized colors, this Data Sheet is giving general properties, some of them may be slightly altered upon color selected.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

#### **Product Characteristics**

Status

Availability

Europe

Injection molding

Features

High melt flow rate, scratch resistance, surface appearance, impact/stiffness balance, UV resistance.

**Typical Customer Applications** Used for automotive unpainted bumper and outdoor/exterior applications.

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	30	g/10 min
Density (23 °C)	ISO 1183-1/A	1	g/cm <sup>3</sup>
Mechanical			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	17	MPa
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1550	MPa
Flexural Strength (23 °C) Tech. A	ISO 178/A1	23	MPa
Impact			
Izod Impact strength, notched (23 °C)	ISO 180/1A	40	kJ/m²
Izod Impact Strength, notched (-30 °C)	ISO 180/1A	6	kJ/m <sup>2</sup>
Thermal			
Vicat Softening Temperature B (50 N)	ISO 306	48	°C
Heat Deflection Temperature A (1.8 MPa)	ISO 75-1, -2	52	°C

### **Product Storage and Handling**

- · Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- · Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

#### **Notes**

Typical properties; not to be construed as specifications.

(1): Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.