(+) 188 1699 6168 hongrunplastics.com



# Hostacom 62F4-2C

## **Compounded Polyolefin**

#### **Product Description**

Hostacom 62F4-2C high melt flow, 1,900 MPa flexural modulus, precolored, 20% talc-filled polypropylene homopolymer has excellent heat aging characteristics, high chemical resistance and easy processability.

### **Product Characteristics**

**Status** Commercial: Active

**Test Method used ASTM** 

**Availability** North America, Asia-Pacific, Australia/NZ, Africa-Middle

East, Latin America

**Processing Methods** Injection Molding

Good Chemical Resistance, Good Colorability, High Flow, **Features** 

Good Heat Aging Resistance, Homopolymer, Good Processability, Good Stiffness, Good Thermal Stability

**Typical Customer Applications** Appliances, Automotive Parts, Hair Dryers, Shavers and

Steam Irons, Housewares

Typical Properties	Method	Value	Unit
Physical			
Density -Specific Gravity	ASTM D 792	1.04	g/cm³
Melt Flow Rate (230°C/2.16kg)	ASTM D 1238	20	g/10 min
Mechanical			
Flexural Modulus	ASTM D 790	1900	MPa
Tensile Strength @ Yield	ASTM D 638	31	MPa
Tensile Strength @ Break	ASTM D 638	26	MPa
Tensile Elongation @ Yield	ASTM D 638	5	%
Tensile Elongation @ Brk	ASTM D 638	20	%
Impact			
Notched Izod Impact (23 °C)	ASTM D 256	27	J/m
Hardness			
Rockwell Hardness (R-Scale)	ASTM D 785	98	
Thermal			
DTUL @66psi - Unannealed	ASTM D 648	116	°C
Additional Information			
Mold shrink, Linear-Flow	ASTM D 955	1.2	%
Note: After 48 hrs at 23°C (Tool).			

# **Additional Properties**

Note: Mold shrinkage values are determined on laboratory injection molded 100 mm x 150 mm x 3.2 mm plaques and, as such, are not necessarily representative of actual field data. Since, for example, wall thickness, gate type and location, flow length and paint oven temperature affect final part dimensions, it is recommended that you contact your Basell representative before any tools are cut.