



Hostacom BB 1161 F/M 2678

Compounded Polyolefin

Product Description

Hostacom BB 1161 F/M 2678 is a 12% talc filled PP copolymer, with high melt flow, excellent processability, high stiffness and high UV resistance. Product is available as a customized color matched, pellet form. This grade is delivered in 2678 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Product Characteristics

Status	Commercial	
Availability	Europe	(1)
Processing Method	Injection molding	
Features	Processability, stiffness, UV resistance.	
Typical Customer Applications	Used for automotive interior trims.	

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	28	g/10 min
Density (23 °C)	ISO 1183-1/A	1.0	g/cm ³
Mechanical			
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1800	MPa
Thermal			
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	106	°C

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

Notes

Typical properties; not to be construed as specifications.

(1) : Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.