(+) 188 1699 6168 hongrunplastics.com



# Hostacom ERC 1218N

## **Compounded Polyolefin**

#### **Product Description**

Hostacom ERC 1218N is a 8% mineral filled, polypropylene copolymer for injection molding. It combines low density with excellent stiffness, scratch resistance, flowability, good impact and dimensional stability. The grade has been specifically designed for molding of automotive interior trim parts.

## **Product Characteristics**

**Status** Development

Test Method used ISO

Availability North America

Processing Methods Injection Molding

Features Good Dimensional Stability, Good Impact Resistance,

Scratch Resistant, High Stiffness

**Typical Customer Applications** Interior Applications

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230°C/2.16kg)	ASTM D 1238	21	g/10 min
Density	ISO 1183	0.95	g/cm³
Mechanical			
Tensile Stress at Yield (23°C)	ISO 527-1, -2	27	MPa
Flexural modulus (23°C)	ISO 178	2100	MPa
Impact			
Charpy notched impact strength	ISO 179		
(-30°C)		2.5	kJ/m²
(23°C)		5	kJ/m²
Thermal			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	105	°C
Additional Information			
Mold shrinkage	ISO 294-4		
Note: Please contact LyondellBasell for shrinkage reco	mmendations.		

## Notes

Typical properties; not to be construed as specifications.