



## Hostacom ERG 320N BLACK

Compounded Polyolefin

IMDS Number: 23542184

### Product Description

Hostacom ERG 320N BLACK is a 30% glass fiber reinforced PP copolymer, with high melt flow rate and high stiffness. The product is available in black color, pellet form.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

### Product Characteristics

Status	Commercial	
Availability	Europe	(1)
Processing Method	Injection molding	
Features	High melt flow rate, stiffness.	
Typical Customer Applications	Used for automotive under-the-hood.	

Typical Properties	Method	Value	Unit
<b>Physical</b>			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	18	g/10 min
Melt Volume Rate (230 °C, 2.16 kg)	ISO 1133	19	cm <sup>3</sup> /10 min
Density (23 °C)	ISO 1183-1/A	1.14	g/cm <sup>3</sup>
<b>Mechanical</b>			
Tensile Modulus (23 °C)	ISO 527-1, -2	6600	MPa
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	85	MPa
<b>Impact</b>			
Charpy Impact Strength, unnotched (23 °C)	ISO 179-1/1eU	40	kJ/m <sup>2</sup>
Charpy Impact Strength, unnotched (0 °C)	ISO 179-1/1eU	40	kJ/m <sup>2</sup>
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	10.5	kJ/m <sup>2</sup>
<b>Thermal</b>			
Vicat Softening Temperature B (50 N)	ISO 306	125	°C
Heat Deflection Temperature A (1.8 MPa)	ISO 75-1, -2	150	°C
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	160	°C

### Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

### Notes

Typical properties; not to be construed as specifications.

(1) : Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.