



## Hostacom ERG719D

### Compounded Polyolefin

#### Product Description

*This information has been secured during the course of product development. Both the product and its properties are subject to change before final commercialization.*

Hostacom ERG719D high melt flow, 4,500 MPa flexural modulus, UV-stabilized, chemically coupled, 30% glass fiber-reinforced polypropylene copolymer has an excellent combination of properties and processability. It was designed for a variety of industrial and automotive applications.

#### Product Characteristics

Status	Commercial: Active
Test Method used	ISO
Availability	North America
Processing Methods	Injection Molding
Features	Copolymer, Good Impact Resistance , Good Moldability , High Rigidity , Good Weather Resistance
Typical Customer Applications	Automotive Parts, Other Industrial

Typical Properties	Method	Value	Unit
<b>Physical</b>			
Density	ISO 1183	1.12	g/cm <sup>3</sup>
Melt flow rate (MFR) (230°C/2.16Kg)	ISO 1133	20	g/10 min
<i>Note: Alternative test method is ASTM D 1238-01.</i>			
<b>Mechanical</b>			
Tensile Stress at Yield	ISO 527-1, -2	57	MPa
Tensile Strain at Break	ISO 527-1, -2	5	%
Flexural modulus	ISO 178	4500	MPa
<b>Impact</b>			
Notched izod impact strength (23 °C)	ISO 180	13	kJ/m <sup>2</sup>
<b>Thermal</b>			
Heat deflection temperature A (1.80 MPa) Unannealed	ISO 75A-1, -2	130	°C

#### Notes

Typical properties; not to be construed as specifications.