(+) 188 1699 6168 hongrunplastics.com



# Hostacom G2 N01

## **Compounded Polyolefin**

# **Product Description**

Hostacom G2 N01 is a 20% milled glass fiber reinforced PP homopolymer without chemical coupling, with low melt flow rate. The product is available as natural, pellet form.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

### **Product Characteristics**

**Status** Commercial

Availability Europe (1)

Processing Method Injection molding

**Features** Low melt flow rate, stiffness.

**Typical Customer Applications** Used for injection moulding general purpose.

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 5 kg)	ISO 1133	8	g/10 min
Melt Volume Rate (230 °C, 5 kg)	ISO 1133	9	cm <sup>3</sup> /10 min
Density (23 °C)	ISO 1183-1/A	1.05	g/cm <sup>3</sup>
Mechanical			
Tensile Modulus (23 °C)	ISO 527-1, -2	3300	MPa
Impact			
Charpy Impact Strength, unnotched (23 °C)	ISO 179-1/1eU	45	kJ/m <sup>2</sup>
Charpy Impact Strength, unnotched (0 °C)	ISO 179-1/1eU	25	kJ/m <sup>2</sup>
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	4	kJ/m <sup>2</sup>
Thermal			
Heat Deflection Temperature A (1.8 MPa)	ISO 75-1, -2	80	°C
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	120	°C

### **Product Storage and Handling**

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- · Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

#### **Notes**

Typical properties; not to be construed as specifications.

(1): Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.