



## Hostacom HKP 438D NAT

### Compounded Polyolefin

#### Product Description

*This grade is not intended for medical, pharmaceutical, food, drinking water and all applications not listed in the supported list. For more information please contact our sales representatives.*

#### Product Characteristics

Status	Under Industrialization	
Availability	Europe	(1)
Processing Method	0	
Features	0	
Typical Customer Applications	0	

Typical Properties	Method	Value	Unit
<b>Physical</b>			
Density (23 °C)	ISO 1183-1/A	1.26	g/cm <sup>3</sup>
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	11	g/10 min
Melt Volume Rate (230 °C, 2.16 kg)	ISO 1133	11	cm <sup>3</sup> /10 min
<b>Mechanical</b>			
Tensile Modulus (23 °C)	ISO 527-1, -2	2800	MPa
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	22	MPa
Tens.Strain at Break	ISO 527-1, -2	>40	%
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	2900	MPa
<b>Impact</b>			
Charpy Impact Strength, unnotched (23 °C)	ISO 179-1/1eU	60	kJ/m <sup>2</sup>
Charpy Impact Strength, unnotched (0 °C)	ISO 179-1/1eU	25	kJ/m <sup>2</sup>
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	2.5	kJ/m <sup>2</sup>
Charpy Impact Strength, notched (0 °C)	ISO 179-1/1eA	1.5	kJ/m <sup>2</sup>
<b>Thermal</b>			
Vicat Softening Temperature B (50 N)	ISO 306	90	°C
Heat Deflection Temperature A (1.8 MPa)	ISO 75-1, -2	56	°C
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	100	°C

#### Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

#### Notes

Typical properties; not to be construed as specifications.

(1) : Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.