(+) 188 1699 6168 hongrunplastics.com



# Hostacom PP 3100 10

## **Compounded Polyolefin**

### **Product Description**

Hostacom PP 3100 10 is an unfilled PP copolymer, with medium melt flow rate and high impact resistance. The product is also available as a customized color matched, pellet form.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

#### **Product Characteristics**

**Status** Commercial

Availability Europe (1)

Processing Method Injection molding

**Features** Medium melt flow rate, impact resistance.

Typical Customer Applications Used for standard applications.

| Typical Properties                      | Method        | Value | Unit                    |
|---|---------------|-------|-------------------------|
| Physical                                |               |       |                         |
| Melt Flow Rate (230 °C, 2.16 kg)        | ISO 1133      | 6     | g/10 min                |
| Melt Volume Rate (230 °C, 2.16 kg)      | ISO 1133      | 8     | cm <sup>3</sup> /10 min |
| Density (23 °C)                         | ISO 1183-1/A  | 0.91  | g/cm <sup>3</sup>       |
| Mechanical                              |               |       |                         |
| Tensile Modulus (23 °C)                 | ISO 527-1, -2 | 1100  | MPa                     |
| Tensile Stress at Yield (23 °C)         | ISO 527-1, -2 | 18    | MPa                     |
| Impact                                  |               |       |                         |
| Charpy Impact Strength, notched (23 °C) | ISO 179-1/1eA | 15    | kJ/m <sup>2</sup>       |
| Thermal                                 |               |       |                         |
| Heat Deflection Temperature A (1.8 MPa) | ISO 75-1, -2  | 55    | °C                      |

## **Product Storage and Handling**

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- · Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- · Keep material completely dry for good processing.

#### **Notes**

Typical properties; not to be construed as specifications.

(1): Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.