

Technical Data Sheet

Hostacom TRC 1193N NATURAL



Polypropylene Compounds

Product Description

Hostacom TRC 1193N NATURAL is high melt flow, 1,900 MPa flexural modulus, low density thermoplastic polyolefin (TPO) resin. It has an excellent balance of processability, rigidity, impact, scratch and mar resistance. It is typically used for injection molding of Instrumental Panels and other interior trim parts or components with good surface appearance properties.

Regulatory Status

For regulatory compliance information, see *Hostacom* TRC 1193N NATURAL [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

| | |
|--------------------------|--|
| Status | Commercial: Active |
| Availability | North America |
| Application | Instrument Panels; Interior Automotive Applications |
| Market | Automotive |
| Processing Method | Injection Molding |
| Attribute | Excellent Processability; Good Moldability; High Flow; High Impact Resistance; High Rigidity; Low Density; Scratch Resistant |

| Typical Properties | Nominal Value | Units | Test Method |
|--|---------------|-------------------|---------------|
| Physical | | | |
| Melt Flow Rate, (230 °C/2.16 kg) | 20 | g/10 min | ISO 1133-1 |
| Density, (23 °C) | 0.99 | g/cm ³ | ISO 1183-1 |
| Mechanical | | | |
| Flexural Modulus | 1900 | MPa | ISO 178 |
| Tensile Stress at Yield | 19 | MPa | ISO 527-1, -2 |
| Tensile Strain at Yield | 6 | % | ISO 527-1, -2 |
| Impact | | | |
| Notched Izod Impact Strength | | | |
| (23 °C) | 45 | kJ/m ² | ISO 180 |
| (-30 °C) | 8 | kJ/m ² | ISO 180 |
| Thermal | | | |
| Deflection Temperature Under Load, (0.45 MPa, Unannealed) | 107 | °C | ISO 75B-1, -2 |
| Additional Information | | | |
| Mold Shrinkage | | | ISO 294-4 |
| Please contact LyondellBasell for shrinkage recommendations. | | | |

Notes

These are typical property values not to be construed as specification limits.