



Hostacom TRC 352N C12546

Compounded Polyolefin

Product Description

Hostacom TRC 352N C12546 is a 20% talc filled PP copolymer, with excellent impact/stiffness balance and good flowability and good scratch resistance outstanding blooming resistance at elevated temperatures. Product is available as a customized color matched, pellet form. This grade is delivered in C12546 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Product Characteristics

Status	Commercial	
Availability	Europe	(1)
Processing Method	Injection molding	
Features	Impact/stiffness balance, flowability, scratch resistance, blooming resistance at elevated temperatures.	

Typical Customer Applications Used for indoor/interior applications.

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	18	g/10 min
Density (23 °C)	ISO 1183-1/A	1.04	g/cm ³
Mechanical			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	22	MPa
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1900	MPa
Impact			
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	30	kJ/m ²
Charpy Impact Strength, notched (-30 °C)	ISO 179-1/1eA	3	kJ/m ²
Charpy Impact Strength, unnotched (23 °C)	ISO 179-1/1eU	NB	kJ/m ²
Thermal			
Heat Deflection Temperature A (1.8 MPa)	ISO 75-1, -2	54	°C

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

Notes

Typical properties; not to be construed as specifications.

(1) : Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.