



Hostacom TRC 399N G21373

Compounded Polyolefin

Product Description

Hostacom TRC 399N G21373 is a 14% talc filled PP copolymer, with excellent impact/stiffness balance, excellent flowability and good UV resistance. Product is available as a customized color matched, pellet form. This grade is delivered in G21373 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Product Characteristics

Status	Commercial	
Availability	Europe	(1)
Processing Method	Injection molding	
Features	Impact/stiffness balance, flowability.	
Typical Customer Applications	Used for applications that require excellent processability and excellent aesthetics properties.	

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	23	g/10 min
Density (23 °C)	ISO 1183-1/A	1.0	g/cm ³
Mechanical			
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1800	MPa
Impact			
Izod Impact strength, notched (23 °C)	ISO 180/1A	38	kJ/m ²
Izod Impact Strength, notched (-30 °C)	ISO 180/1A	5	kJ/m ²

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affect the quality of this product
- Keep material completely dry for good processing.

Notes

Typical properties; not to be construed as specifications.

(1) : Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.