

Technical Data Sheet

Hostacom TRC 411N C11515



Polypropylene Compounds

Product Description

Hostacom TRC 411N is a 15% talc filled elastomer modified PP, with high flowability, good impact/stiffness balance, outstanding scratch resistance, low odour and low emissions. This grade is delivered in customer customized colors, this Data Sheet is giving general properties, some of them may be slightly altered upon color selected.

Regulatory Status

For regulatory compliance information, see Hostacom TRC 411N C11515 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Status	Commercial: Active
Availability	Europe
Application	Automotive Parts; Instrument Panels; Interior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	Ductile; Good Abrasion Resistance; Good Color Stability; Good Processability; Good Stiffness; Good Surface Finish; High Flow; High Impact Resistance; Low Density; Low Temperature Impact Resistance; Low to No Odor; Low VOC Emission; Pleasing Surface Appearance; Scratch Resistant; UV Resistant

Typical Properties	Nominal		Test Method
	Value	Units	
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	19	g/10 min	ISO 1133
Density, (23 °C)	1.02	g/cm³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1800	MPa	ISO 178/A1
Impact			
Charpy Impact Strength - Notched, (23 °C)	30	kJ/m²	ISO 179-1/1eA
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	90	°C	ISO 75B-1, -2

Notes

These are typical property values not to be construed as specification limits.