



Hostacom TRC 411N

Compounded Polyolefin

Product Description

Hostacom TRC 411N is a 15% talc filled elastomer modified PP, with high flowability, good impact/stiffness balance, outstanding scratch resistance, low odour and low emissions. This grade is delivered in customer customized colors, this Data Sheet is giving general properties, some of them may be slightly altered upon color selected.

This grade is not intended for medical, pharmaceutical, food, drinking water and all applications not listed in the supported list. For more information please contact our sales representatives.

Product Characteristics

Status	Commercial
Availability	Europe (1)
Processing Method	Injection molding
Features	Flowability, impact/stiffness balance, scratch resistance, low odour, low emissions.
Typical Customer Applications	Used for applications that require excellent aesthetics, used for automotive instrument panel and automotive interior trims, that require good balance of stiffness and impact performance

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	19	g/10 min
Density (23 °C)	ISO 1183-1/A	1.02	g/cm ³
Mechanical			
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1800	MPa
Impact			
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	30	kJ/m ²
Thermal			
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	90	°C

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

Notes

Typical properties; not to be construed as specifications.

(1) : Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.