



Hostacom X M1 T01 156505 DA

Compounded Polyolefin

Product Description

Hostacom X M1 T01 156505 DA is a 10% talc filled PP copolymer, with high flowability, high toughness, excellent scratch resistance, low odour and low emissions. Product is available as a customized color matched, pellet form. This grade is delivered in 156505 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Product Characteristics

Status	Commercial	
Availability	Europe	(1)
Processing Method	Injection molding	
Features	Flowability, scratch resistance, low emissions.	
Typical Customer Applications	Used for automotive instrument panel.	

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	5.5	g/10 min
Density (23 °C)	ISO 1183-1/A	0.97	g/cm ³
Mechanical			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	19	MPa
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1200	MPa
Impact			
Charpy Impact Strength, unnotched (23 °C)	ISO 179-1/1eU	NB	kJ/m ²
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	35	kJ/m ²
Charpy Impact Strength, notched (-30 °C)	ISO 179-1/1eA	5	kJ/m ²
Thermal			
Vicat Softening Temperature A (10 N)	ISO 306	137	°C
Heat Deflection Temperature A (1.8 MPa)	ISO 75-1, -2	55	°C

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

Notes

Typical properties; not to be construed as specifications.

(1) : Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.