(+) 188 1699 6168 hongrunplastics.com



# Hostacom X M4 U16 201104

## **Compounded Polyolefin**

## **Product Description**

Hostacom X M4 U16 201104 is a mineral filled PP homopolymer, with medium melt flow rate.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

#### **Product Characteristics**

**Status** Commercial

Availability Europe (1)

Processing Method Injection molding

**Features** Medium melt flow rate. **Typical Customer Applications** Used for appliances.

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	13	g/10 min
Density (23 °C)	ISO 1183-1/A	1.28	g/cm <sup>3</sup>
Melt Volume Rate (230 °C, 2.16 kg)	ISO 1133	12	cm <sup>3</sup> /10 min
Mechanical			
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	2600	MPa
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	21	MPa
Tensile Modulus (23 °C)	ISO 527-1, -2	2500	MPa
Tensile Strain at Yield (23 °C)	ISO 527-1, -2	3.5	%
Impact			
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	2.5	kJ/m <sup>2</sup>
Charpy Impact Strength, unnotched (23 °C)	ISO 179-1/1eU	40	kJ/m <sup>2</sup>
Thermal			
Heat Deflection Temperature A (1.8 MPa)	ISO 75-1, -2	59	°C

#### **Product Storage and Handling**

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

### **Notes**

Typical properties; not to be construed as specifications.

(1): Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.