

Technical Data Sheet

POLYTROPE® STR 3567EU-01 CLEAR

Enhanced Polyolefin (Capstock Resin)
Engineering Plastics

Product Description

POLYTROPE STR 3567EU resin is a medium gloss, weatherable, olefin cap resin providing exceptional durability. It is specifically designed for the co-extrusion process as a cap resin over POLYTROPE STR enhanced polyolefin TPO and FR TPO base resins. It is especially suited for thermoformed applications, as it maintains its' smooth surface and uniform gloss through the thermoforming process. POLYTROPE STR 3567EU-01 CLEAR can be used as a clear cap or it can be easily colored. The durability of the cap resin enables it match or exceed the performance of acrylic resins, laminated films, and paint coatings.

General			
Features	• Chemical Resistant • Durable • High Scratch Resistance	• Low Temperature Impact Resistance • Recyclable Material • Stain Resistant	• Weather Resistant
Forms	• Pellets		
Processing Method	• Coextrusion • Extrusion	• Profile Extrusion • Sheet Extrusion	• Thermoforming

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity ¹	0.900	0.898 g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.5 g/10 min	2.5 g/10 min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Stress ² (Yield, 73°F (23°C))	6110 psi	42.1 MPa	ISO 527-2
Tensile Strain ² (Break, 451°F (233°C))	200 %	200 %	ISO 527-2
Flexural Modulus - Chord ³ (73°F (23°C))	300000 psi	2070 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Instrumented Dart Impact			ASTM D3763
73°F (23°C), Total Energy, Ductile Failure	410 in-lb	46.3 J	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Heat Deflection Temperature			ISO 75-2/Bf
66 psi (0.45 MPa), Unannealed	198 °F	92.2 °C	
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.13 in (3.2 mm), All Colors)	HB	HB	UL 94
Optical	Nominal Value (English)	Nominal Value (SI)	Test Method
Gardner Gloss			ISO 2813
60°, 125 mil (3180 µm), Thermoformed, Smooth	60 to 70	60 to 70	

Notes

¹ Method A

² Type 1, 2.0 in/min (50 mm/min)

³ Type 1A, 0.079 in/min (2.0 mm/min)

Notes

These are typical property values not to be construed as specification limits.