

Technical Data Sheet

Polyfort TPO-15T BK2030BLK



Polyolefin, Unspecified

Product Description

15% Mineral Filled Thermoplastic Polyolefin Melt Flow Adjustable for Application Colors Available Add "U" for UV Stabilized Add "H" for Heat Stabilized

Filler/Reinforcement Mineral, 15%

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate	18	g/10 min	ASTM D1238
Density - Specific Gravity	1.04	g/cm ³	ASTM D792
Mechanical			
Tensile Strength at Yield	20.7	MPa	ASTM D638
Flexural Modulus	1380	MPa	ASTM D790
Impact			
Notched Izod Impact	370	J/m	ASTM D256