

Technical Data Sheet

Polyfort TPO-23T BK(10M)BLK



Polypropylene, Compounded (TPO)

Product Description

TPO-23T BK (10M) is a 23% Talc-Filled Polypropylene

Appearance Black
Filler/Reinforcement Talc, 23%

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate	11	g/10 min	ASTM D1238
Mechanical			
Flexural Modulus	1450	MPa	ASTM D790
Impact			
Gardner Impact	18.6	J	ASTM D5420
Thermal			
Deflection Temperature Under Load Unannealed (264 psi)	116	°C	ASTM D648