



## Sequel 1980-PUV

### Compounded Polyolefin

#### Product Description

*Sequel* 1980-PUV high melt flow, high flexural modulus, UV-stabilized, mineral-filled, thermoplastic elastomeric olefin has an excellent balance of properties and processability.

#### Product Characteristics

|                               |                                                        |
|-------------------------------|--------------------------------------------------------|
| Status                        | Commercial: Active                                     |
| Test Method used              | ISO                                                    |
| Availability                  | North America                                          |
| Processing Methods            | Injection Molding                                      |
| Features                      | Good Flow , Good Moldability , Good Weather Resistance |
| Typical Customer Applications | Bumpers, Exterior Applications                         |

| Typical Properties                                                        | Method      | Value | Unit              |
|---------------------------------------------------------------------------|-------------|-------|-------------------|
| <b>Physical</b>                                                           |             |       |                   |
| Melt Flow Rate (230°C/2.16kg)                                             | ASTM D 1238 | 25    | g/10 min          |
| Density (Method A)                                                        | ISO 1183    | 1.04  | g/cm <sup>3</sup> |
| <b>Mechanical</b>                                                         |             |       |                   |
| Flexural modulus (23 °C)                                                  | ISO 178     | 1700  | MPa               |
| <b>Additional Information</b>                                             |             |       |                   |
| Mold shrinkage                                                            | ISO 294-4   |       |                   |
| <i>Note:</i> Please contact LyondellBasell for shrinkage recommendations. |             |       |                   |

#### Notes

Typical properties; not to be construed as specifications.