



Softell TKG 300N G42669

Compounded Polyolefin

IMDS Number:

35491870

Product Description

Softell TKG 300N G42669 is an 8% glass fiber reinforced PP copolymer, with good dimensional stability, low gloss, good UV resistance, high stiffness and excellent scratch resistance. Product is available as a customized color matched, pellet form. This grade is delivered in G42669 color version.

This grade is not intended for medical, pharmaceutical, food, drinking water and all applications not listed in the supported list. For more information please contact our sales representatives.

Product Characteristics

Status	Under Industrialization	
Availability	Europe	(1)
Processing Method	Injection molding	
Features	Dimensional stability, gloss, stiffness, scratch resistance.	
Typical Customer Applications	Used for automotive interior applications that require low gloss appearance.	

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	6	g/10 min
Density (23 °C)	ISO 1183-1/A	1.09	g/cm ³
Mechanical			
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	2500	MPa
Impact			
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	35	kJ/m ²
Charpy Impact Strength, notched (-30 °C)	ISO 179-1/1eA	7.5	kJ/m ²
Thermal			
Heat Deflection Temperature A (1.8 MPa)	ISO 75-1, -2	80	°C

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

Notes

Typical properties; not to be construed as specifications.

(1) : Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.