(+) 188 1699 6168 hongrunplastics.com



Softell TKG 300NU

Compounded Polyolefin

Product Description

Softell TKG 300NU is a medium melt flow, very high flexural modulus, UV-stabilized, 25% glassfiber reinforced thermoplastic polyolefin compound for injection molding. TKG 300NU has been especially designed for aesthetical automotive interior applications.

Product Characteristics

Status Commercial: Restricted

Test Method used ISO

Availability North America

Processing Methods Injection Molding

Features Ductile, Low Gloss, High Impact Resistance , Scratch

Resistant, Low Shrinkage, Soft, Sound Damping

Typical Customer Applications Interior Applications

Typical Properties	Method	Value	Unit
Physical			
Density	ISO 1183	1.07	g/cm³
Melt flow rate (MFR) (230°C/2.16kg)	ISO 1133	8	g/10 min
Mechanical			
Flexural modulus (23°C)	ISO 178	2600	MPa
Impact			
Notched izod impact strength	ISO 180		
(23°C)		30	kJ/m²
(-30°C)		12	kJ/m²
Additional Information			
Mold shrinkage	ISO 294-4		
Note: Please contact LyondellBasell for shrin	kage recommendations	i.	

Notes

Typical properties; not to be construed as specifications.