

# Toppyl SP2102C

# **Compounded Polyolefin**

#### **Product Description**

**Toppyl SP 2102C** is a fully formulated seal peel solution developed for the cast and blown film technology.

This product has been designed to offer a peelable seal to PP substrates for non - sterilisable applications.

Toppyl SP 2102 C is a solution created to replace completely the sealing layer in a coextruded film

It provides a constant easy-opening force over a wide sealing temperature window and is readily processable on conventional equipment in both mono and co-extruded structures.

 ${\sf EU}$  and FDA compliance information about this product can be found in separate product documentation.

This product is not intended for use in medical and pharmaceutical applications.

# **Product Characteristics**

Status Commercial: Active

Test Method used ISC

Availability Europe, North America, Asia-Pacific, Australia/NZ, Africa-

Middle East, Latin America

Features Medium Antiblocking , Semi Crystalline, Good Heat Seal,

Medium Slip

**Typical Customer Applications** Blown Film, Cast Film, Peelable Film, Speciality Film

Typical Properties	Method	Value	Unit
Physical			
Density	ISO 1183	0.904	g/cm³
Melt flow rate (MFR)	ISO 1133	5.7	g/10 min
Note: Melt flow rate 230 Deg. C / 2.16 kg			
Mechanical			
Tensile Strength @ Brk MD	ASTM D 882	32	MPa
Tensile Strength @ Yld MD	ASTM D 882	19	MPa
Elongation at break MD	ASTM D 882	750	%
Thermal			
Vicat softening temperature A/50	ISO 306	96	°C
Film			
Coefficient of Friction	ASTM D 1894	0.30	
Note: Dynamic COF			
Secant modulus MD (2% Secant)	ASTM D 882	380	MPa

### **Additional Properties**

Recommended processing temperatures:  $185^{\circ}$ C to  $265^{\circ}$ C In cases were higher temperatures are required please contact your appropriate technical contact for support.

#### Notes

 $\label{typical properties: not to be construed as specifications.} \\$