

Micromax™ 1748R

Electronic Inks and Pastes

Series Resistors System HR Compositions

Micromax™ 17G-Series screen printable resistor compositions are specially formulated and tested for use on gold conductor terminations. These compositions range from 3 Ω /sq to 1 M Ω /sq. Each member is blendable with the adjacent members. There are no blend breaks. The length effects have been characterized for very small resistors.

Product benefits

- Qualified and tested on Au conductor
- Excellent encapsulated and unencapsulated post laser trim stability after laser trimming and long term storage
- Optimised for 60 minute 850 °C firing profile
- Fully blendable resistor series
- Phthalate, Cadmium, Nickel oxide free*

* Phthalate, Cadmium and Nickel oxide 'free' as used herein means that cadmium, phthalate and nickel oxide are not intentional ingredients in and are not intentionally added to the referenced product. Trace amounts however may be present.

Product information

Solvent or thinner	Micromax™ 4036
Blend member or series	17Gsrs

Rheological properties

Viscosity	145 - 210 ^[1] Pa.s
[1]: Brookfield HAT, UC&SP, SC4-14/6R, 10 rpm, 25 °C $\pm$ 0.2 °C	

Application technique

Mask mesh	200 ^[2]
Mask emulsion	12 - 18 ^[2] μ m
Drying time	10 - 15 min
Drying temperature	150 °C
Theoretical coverage	80 - 110 ^[3] cm ² /g
Recommended film thickness, dried	22 - 28 μ m
Leveling time	$\geq$ 10 min

[2]: Screen Types: Stainless steel

[3]: based on wet thickness of 50 μ m

Micromax™ 1748R

Electronic Inks and Pastes

Electrical properties

Surface resistivity	9E7 - 1.1E8 ^[4] mOhm per square
Hot Temperature Coefficient Resistance	-100 - 100 ^[5] ppm/K
Cold Temperature Coefficient Resistance	-100 - 100 ^[6] ppm/K
Noise	2 ^[7] dB
Short Term Overload Voltage	280 ^[8] V/mm
Standard Working Voltage	110 ^[9] V/mm
Maximum Rated Power Dissipation	120 ^[10] m/(W.mm ²)

[4]: Shipping specifications : Reported to Dried thickness 25µm. Fired on Micromax™ 5715 Au prefired termination. Resistor geometry : 1.5 mm x 1.5 mm. Firing : 60-min cycle to peak temperature of 850°C for 10 min. All tests performed on 96% alumina substrate.

[5]: temperature coefficient of resistance : 25 to 125°C

[6]: temperature coefficient of resistance : -55 to 25°C

[7]: resistor geometry : 1mm x 1mm; firing cycle : 60 min cycle to peak temperature of 850°C for 10 min

[8]: short term overload voltage : voltage required (5 sec duration) to induce a resistance change of 0.25% in a 1mm x 1mm trimmed resistor at 25°C

[9]: standard working voltage : 0.4 x short term overload voltage

[10]: maximum rated power = (standard working voltage)² / resistance

Storage and stability

Shelf life	6 ^[11] months
------------	--------------------------

[11]: in unopened containers, from date of shipment, at temperature between 5-30°C

Additional information

How to use

Design & compatibility

• Compatibility

- Whilst Micromax™ has tested this composition with the materials specified above and the recommended processing conditions, it is impossible or impractical to cover every combination of materials, customer processing conditions and circuit layouts. It is therefore essential that customers thoroughly evaluate the material in their specific situations in order to completely satisfy themselves with the overall quality and suitability of the composition for its intended application(s).

Processing

• Terminations

- Use of a different termination material may cause a shift of TCR and resistivity values from those stated.

• Blendability

Micromax™ 1748R

Electronic Inks and Pastes

- Adjacent members of Micromax™ 17G-Series are blendable.
- **Substrates**
 - Substrates of different compositions and from various manufacturers may result in variations in performance properties.
- **Screen types**
 - 200 mesh stainless steel screen with a 12-18µm emulsion build up. Nylon or polyester screens may be used in some applications. A 150-175 mesh screen will usually be required to achieve equivalent print thickness.
 - Recommended dried thickness 25+/-3µm.
- **Printing**
 - The composition should be thoroughly mixed before use. This is best achieved by slow, gentle hand stirring with a clean burr-free spatula (flexible plastic or stainless steel) for about 1-2 minutes. Care must be taken to avoid air entrapment. Printing should be performed in a well ventilated area.
 - Note : Optimum printing characteristics are generally achieved in the room temperature range of 20°C - 23°C. It is therefore important that the material, in its container, is at the temperature prior to commencement of printing. Class 10,000 printing area is recommended for building complex hybrids and multilayer circuits, otherwise severe yield losses could occur.
- **Thinning**
 - Micromax™ 17G-Series compositions are optimized for screen printing and thinning is not normally required. Use the Micromax™ recommended thinner for slight adjustments to viscosity or to replace evaporation losses. The use of too much thinner or the use of a non-recommended thinner may affect the rheological behaviour of the material and its printing characteristics.
- **Drying**
 - Allow prints to level for over 10 minutes at room temperature, then dry for ≥ 10-15 minutes at 150°C.
 - Dry in a well ventilated oven or conveyor dryer.
- **Firing**
 - 850°C peak held for 10 minutes on 60 minute cycle in an air atmosphere. Micromax™ 17G-Series resistivity and TCR specifications are based on a 60-min firing cycle with a 10 min peak at 850°C, 20 min above 800°C and 30 min above 600°C.
 - Fire in well ventilated belt, conveyor furnace or static furnace. Air flows and extraction rates should be optimized to ensure that oxidizing conditions exist within the muffle and that no exhaust gases enter the room.
- **Encapsulant**
 - In general, glass encapsulation is not required. However, in applications which require mechanical protection or protection

Micromax™ 1748R

Electronic Inks and Pastes

from extreme environments such as high temperature nitrogen or forming gas, Micromax™ encapsulant compositions QQ550 and QQ620 are recommended.

- **Resistor geometry**

- Micromax™ 17G-Series compositions are quality Assured tested using a 1.5mm x 1.5mm resistor with prefired Micromax™ Au termination. Variations in resistor geometry will result in slight variations of resistivity and TCR values. Length effect curves are based on tests of 0.5-1.5 mm wide resistors varying in aspect ratio from 0.4 - 4.0sq.

Properties

- All values reported here are results of experiments in our laboratories intended to illustrate product performance potential with a given experimental design. They are not intended to represent the product's specifications, details of which are available upon demand.

General

Performance will depend to a large degree on care exercised in screen printing. Scrupulous care should be taken to keep the composition, printing screens and other tools free of metal contamination. Dust, lint and other particulate matter may also contribute to poor yields.

Storage and shelf life

Containers may be stored in a clean, stable environment at room temperature (between 5°C – 30°C) with their lids tightly sealed. Storage in high temperature (>30°C) or in freezers (temperature <0°C) is NOT recommended as this could cause irreversible changes in the material. The shelf life of compositions in factory-sealed (unopened) containers between (5°C – 30°C) is 6 months from date of shipment.


Safety and handling

For safety and handling information pertaining to this product, read Safety Data Sheet (SDS).

Micromax™ 1748R

Electronic Inks and Pastes

Chart 1. Firing Profile




Micromax™ 1748R

Electronic Inks and Pastes

Figure 2. Blending Characteristics

Adjacent members of 17G-Series are blendable. Resistivities and TCRs blend smoothly and predictably for all blend ratios.

The data required in these curves were generated using resistors terminated with prefired 5715 Au Conductor.



Micromax™ 1748R

Electronic Inks and Pastes

Printed: 2023-09-21

Page: 8 of 8

Revised: 2023-06-27 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2023 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC. KEPITAL is a registered trademark of Korea Engineering Plastics Company, Ltd.