

Micromax™ 5018G

Electronic Inks and Pastes

UV Curable Dielectric

Polymeric dielectric composition Micromax™ 5018G is a green UV curable, solvent less, screen printable composition used in encapsulant and crossover applications for both rigid and flexible circuit manufacture. It offers the advantages of rapid cure and excellent processing latitude while maintaining excellent electrical and physical properties after cure, including excellent crosshatch adhesion to print-treated and good adhesion to non-print-treated PET substrate and conductor. It is fully compatible with Micromax™ 5000's Series conductor compositions.

Product benefits

- Best insulating UV cure dielectric

Product information

Colour	Green
Odour	Slight ^[1]
Solvent or thinner	Not recommended
Density	1.28 g/cm ³
Solid content	100 ^[2] %
Maximum Service Temperature	70 ^[3] °C
[1]: Slight, pleasant	
[2]: 150 °C	
[3]: on Polyester Film	

Rheological properties

Viscosity	15 - 30 ^[4] Pa.s
[4]: Brookfield 1/2RVT, 10 rpm #14 spindle, 25 °C	

Application technique

Mask mesh	200 - 280
Theoretical coverage	290 ^[5] cm ² /g
Recommended film thickness	25.4 - 30.5 ^[6] µm
[5]: at 25.4µm, coating given by 280-mesh stainless steel	
[6]: after UV cure	

Typical mechanical properties

Adhesion, cross hatch	5B ^[7] class
[7]: The same result, Dielectric to Polyester Scotch Tape #600 and Conductor to Dielectric, ASTM D3359-78.	

Micromax™ 5018G

Electronic Inks and Pastes

Electrical properties

Dielectric Constant	4.4 ^[8]
Insulation Resistance, DC	≥1E10 ^[9] Ohm
Breakdown Voltage	≥500 ^[10] V

[8]: ASTM D150, at 1 KHz

[9]: sq at 25.4μm

[10]: ASTM D150, V/25.4μm DC

Storage and stability

Shelf life	6 ^[11] months
------------	--------------------------

[11]: in unopened containers, from date of shipment, at temperature <25°C

Additional information

How to use

Processing

- **Substrates**
 - Polyester, polyimide, epoxy glass
- **Screen types**
 - Polyester, stainless steel
- **Printing**
 - Semiautomatic and manual
- **Typical thickness (after cure)**
 - Printed with 200 - 280 mesh stainless steel screen
 - 1 - 1.2 mil
 - Two prints of dielectric are strongly recommended to achieve maximum circuit reliability.
- **Work life**
 - > 2 hours
- **Curing**
 - 40 ft/min in air
 - RPC Industries "QC" Processor Model 1202 AN, with the 200 W/in medium- pressure mercury vapor lamps. Since cure conditions govern characteristics, customers should establish the cure rate required to produce optimum combination of flexibility and hardness.
 - 500 - 1500 mJ/cm
 - 0.500 - 1.500, joules using International Light IL.390B Light Bug or UV Process Supply.

Properties

Typical Physical & Electrical Properties on Polyester Film & Composition Properties

Micromax™ 5018G

Electronic Inks and Pastes

Test	Properties
Abrasion Resistance, Pencil Hardness (ASTM D3363-74) [H]	≥ 1
Flexibility (180° crease over Micromax™ 5007)	No opens
Change in Physical Properties after Environmental Tests*	Insignificant
Change in Insulation Properties after Environmental Tests*	May drop up to one order of magnitude
Coverage (cm ² /g) (Dependent on print thickness) 0.45 mil coating given by 280-mesh polyester	500
Coverage (cm ² /g) (Dependent on print thickness) 0.6 mil coating given by 230-mesh polyester	375
Coverage (cm ² /g) (Dependent on print thickness) 1.1 mil coating given by 200-mesh stainless steel	240

* Environmental Tests

- Thermal Shock (+85°C to -40°C, 30 min. each, 5 cycles)
- Dry Heat (+85°C, 10 days)
- Humidity (+40°C, 95%RH, 10 days) (MIL Std 202E, method 103, cond. A)
- Salt Spray (+35°C, 5% salt, 10 days) (ASTM B117)

Information in this datasheet shows anticipated typical physical properties for Micromax™ 5018G based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

Storage and shelf life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25°C). Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use. UV curable compositions such as Micromax™ 5018G should be stored away from heat and light.

Micromax™ 5018G

Electronic Inks and Pastes

Safety and handling

For safety and handling information pertaining to this product, read Safety Data Sheet (SDS).

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2023 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC. KEPITAL is a registered trademark of Korea Engineering Plastics Company, Ltd.