

Micromax™ 5091D

Electronic Inks and Pastes

PTC Thermistor Composition

Micromax™ 5091D, Micromax™ 5092D and Micromax™ 5093D positive temperature coefficient (PTC) Thermistor compositions are intended for making PTC Thermistor in thick film microcircuits using conventional thick film processing. Potential applications include temperature sensors, temperature compensation elements, and heaters.

Product benefits

- Linear dependence of resistance with temperature
- Compatibility with thick film processing
- Blendability
- High positive TCR
- Laser trim stability
- Environmental stability

Product information

Solvent or thinner	Micromax™ 4553
Blend member or series	5091D/5092D/5093D

Rheological properties

Viscosity	150 - 250 ^[1] Pa.s
[1]: Brookfield HAT, UC&SP, 10 rpm, 25 °C	

Application technique

Mask mesh	200
Mask emulsion	12 - 18 µm
Drying time	10 - 15 min
Drying temperature	150 °C
Recommended film thickness, dried	23 - 27 µm
Leveling time	5 - 10 min

Electrical properties

Surface resistivity	9000 - 11000 ^[2] mOhm per square
Hot Temperature Coefficient Resistance	2900 - 3300 ^[3] ppm/K
Cold Temperature Coefficient Resistance	2900 - 3300 ^[4] ppm/K

[2]: Terminations Ag/Pd 7484; Substrate 96% alumina; Printing 200-mesh stainless steel screen (15±3 µm emulsion thickness) to a dried thickness 25±2 µm; Firing - recommended short profile to a peak temperature of 850 °C for 10 minutes. Resistor geometry for R, laser trim stability: 1.5 x 1.5 mm.

[3]: Resistor geometry for TCR, laser trim stability: 1.5 x 1.5 mm. Measured from +25 to +125 °C.

[4]: Resistor geometry for TCR, laser trim stability: 1.5 x 1.5 mm. Measured from -55 to +25 °C.

Micromax™ 5091D

Electronic Inks and Pastes

Storage and stability

Shelf life

6^[5] months

[5]: in unopened containers, from date of shipment, at temperature <25 °C

Additional information

How to use

Processing

- **Terminations**

- Reported properties are based on tests with Micromax™ 7484 Ag/Pd conductor composition, prefired at 850 °C. Excellent results have also been obtained using Ag Micromax™ 6160, prefired at 850 °C.

- **Substrates**

- Properties are based on tests on 96% alumina substrates. Substrates of other compositions and from various manufacturers may result in variations in performance properties.

- **Printing**

- Specified properties are based on resistors printed to 25±2µm dried print thickness. This is readily achieved using 200-mesh stainless steel screens with 15±3µm emulsion thickness.

- **Drying**

- Prints should be allowed to level 5-10 minutes at room temperature and then dried 10-15 minutes at 150 °C.

- **Firing**

- Resistivity and TCR specifications are based on the recommended 30 minutes firing profile with a 10 minute peak at 850 °C. Slight variation in resistance and TCR will occur when longer firing profiles or higher peak temperature are used.


- **Encapsulant**

- In general, glass encapsulation is not required. However, for applications in need of mechanical protection or protection from extreme environments such as high temperature nitrogen or forming gas, encapsulant Micromax™ 9137, or QQ550 fired at 500 °C is recommended.

Micromax™ 5091D

Electronic Inks and Pastes

FIGURE 1. 30 MINUTES PROFILE



Properties

Typical PCT Thermistor Properties

Test	Properties
Post Laser Trim Stability*1 (%) 25°C/1000 hours	< 0.3
Post Laser Trim Stability*1 (%) 85%RH/85°C/1000 hours	< 0.2
Post Laser Trim Stability*1 (%) 150°C/1000 hours	< 0.3

*1 This data is based on tests of 1.5 x 1.5mm resistors trimmed to 1.5 x initial value with a single plunge cut. All resistors were un-encapsulated.

Information in this datasheet shows anticipated typical physical properties for Micromax™ 5091D, 5092D & 5093D based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

Storage and shelf life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25°C). Shelf life of material in unopened containers is six months

Micromax™ 5091 D

Electronic Inks and Pastes

from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Safety and handling

For safety and handling information pertaining to this product, read Safety Data Sheet (SDS).

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2023 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC. KEPITAL is a registered trademark of Korea Engineering Plastics Company, Ltd.