

Micromax™ 5448

Electronic Inks and Pastes

Carbon Conductive Composition

Micromax™ 5448 is a polymer-based, platable carbon paste printable on a variety of substrates. This composition usually will be applied over a fired-on silver that provides sulfur-proof layer for chip components.

Product benefits

- Excellent conductivity
- Excellent printed resolution
- Good adhesion on both fired silver and alumina substrates
- Good platability
- Cadmium, Lead, Nickel and Phthalate free*

*Cadmium, Lead, Nickel and Phthalate 'free' as used herein means that cadmium, lead, nickel, and phthalate are not intentional ingredients in and are not intentionally added to the referenced product. Trace amounts however may be present.

Product information

Solvent or thinner	Micromax™ 9245
Solid content	50 - 56 ^[1] %
[1]: 150 °C	

Rheological properties

Viscosity	60 - 80 ^[2] Pa.s
[2]: Brookfield HBT, SC4-14/6R, 10 rpm, 25 °C	

Application technique

Mask mesh	250
Mask emulsion	10 - 15 µm
Drying time	10 min
Drying temperature	150 °C
Recommended film thickness, dried	10 - 15 µm
Leveling time	5 min

Electrical properties

Surface resistivity	5000 - 15000 ^[3] mOhm per square
[3]: at 25.4µm	

Micromax™ 5448

Electronic Inks and Pastes

Storage and stability

Shelf life

3^[4] months

[4]: in unopened containers, from date of shipment, at temperature between 0-5 °C

Additional information

How to use

Processing

- **Substrates**
 - Ceramic, glass, Cu foil, glass epoxy, paper
- **Printing**
 - 10-15µm cured thickness can be achieved using 250 mesh stainless steel screen with an emulsion thickness of 10-15µm.
- **Drying**
 - Allow wet prints to level for 5 minutes at room temperature. Dry 10 minutes at 150 °C in a well-ventilated oven, or belt dryer. Drying process can be skipped and directly cured depending on the application.
- **Curing**
 - This composition is best cured at 200 °C for 10 minutes or 180 °C for 30 minutes. Variation in the curing temperature may result in variation in the final properties.
- **Plating**
 - Chips terminated with Micromax™ 5448 and processed as recommended can be electroplated in conventional processes.

Properties

- Information in this datasheet shows anticipated typical physical properties for Micromax™ 5448 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

Storage and shelf life

Shelf life is three months from date of shipment when refrigerated (0-5 °C).

Storage at room temperature is not recommended. Materials should be allowed to equilibrate to room temperature before opening to prevent pick up of moisture from condensation.

After the containers are opened, use and storage conditions and the possible effects of contamination make shelf limits unpredictable.

Micromax™ 5448

Electronic Inks and Pastes

Safety and handling

For safety and handling information pertaining to this product, read Safety Data Sheet (SDS).

Printed: 2023-09-21

Page: 3 of 3

Revised: 2023-05-29 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2023 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC. KEPITAL is a registered trademark of Korea Engineering Plastics Company, Ltd.