

# Micromax™ Intexar™ PE876

## Electronic Inks and Pastes

### Washable Silver Electrode

Micromax™ Intexar™ PE876 is a washable, silver electrode paste for printed low-voltage circuitry on elastomeric film and textile substrates. Due to its proprietary resin system, Micromax™ PE876 possesses excellent bend ability, adhesion, and conduction. It is compatible with polyurethane (TPU) film and select synthetic fabrics.

### Product benefits

- Highly washable
- Improved bend-ability and crease performance
- Compatible with wide variety of fabric and film substrates
- Compatible with lamination

### Product information

Solvent or thinner	Micromax™ 8264
Density	2.41 g/cm <sup>3</sup>
Solid content	66 - 72 <sup>[1]</sup> %
[1]: 150 °C	

### Rheological properties

Viscosity	55 - 75 <sup>[2]</sup> Pa.s
[2]: Brookfield RVT, #14 spindle, 10 rpm, 25 °C	

### Application technique

Mask mesh	200 - 325 <sup>[3]</sup>
Drying time	15 min
Drying temperature	130 °C
Recommended film thickness, dried	5 - 10 <sup>[4]</sup> μm
[3]: Screen Types: Stainless steel	
[4]: at 280 mesh	

### Typical mechanical properties

Adhesion, cross hatch	5B <sup>[5]</sup> class
[5]: No Transfer. ASTM D3359-78, w/3M Scotch Tape 600	

# Micromax™ Intexar™ PE876

## Electronic Inks and Pastes

### Electrical properties

Surface resistivity	$\leq 65^{[6]}$ mOhm per square	
Resistivity retention after crease, 180 °C, 1 cycle, 2kg	$20^{[7]}$ %	ASTM F 1683
[6]: at 25µm, 8µm dried print thickness on ST505 PET film		
[7]: ASTM F1683, 180degc, 1 cycle, 2kg		

### Storage and stability

Shelf life	$6^{[8]}$ months
[8]: in unopened containers, from date of shipment, at temperature <25 °C	

### Additional information

How to use

### Processing

- **Substrates**
  - Select synthetic fabrics
  - Coated fabrics & membranes
  - Thermoplastic polyurethane films
  - Micromax™ PE876 is appropriate for many types of thermally-stable substrates in wearable electronics applications. Due to the diverse nature of potential fabrics and films that could be considered, it is not always possible to provide detailed performance guidance. For more information, please call your local Micromax™ representative.
- **Screen types**
  - 325-200 wire/inch stainless steel mesh
  - 120-77 thread/cm polyester mesh
- **Printing**
  - Automatic reel-to-reel
  - Semi-automatic flat-bed
  - Rotary screen/cylinder screen
- **Thinning**
  - Thinning with Micromax™ 8264 may be desired in some cases depending on printing requirements.
- **Clean-up solvent**
  - Ethylene diacetate
- **Drying**
  - Dry at 130 °C for 15 minutes in a well-ventilated oven or conveyor dryer, where the exhaust meets environmental regulations. Drying efficiency and good print quality/thickness control helps ensure best electrical and physical performance.

# Micromax™ Intexar™ PE876

## Electronic Inks and Pastes

- **Encapsulant**
  - Micromax™ PE773

### Properties

#### Typical Physical Properties

Test	Properties
Abrasion Resistance, Pencil Hardness (ASTM D3363-74) [H]	7

Printed on Melinex ST505 Polyester Film. Information in this datasheet shows anticipated typical physical properties for Micromax™ Intexar™ PE874 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

### Storage and shelf life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25 °C). Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

### Safety and handling

For safety and handling information pertaining to this product, read Safety Data Sheet (SDS).