

Micromax™ LL500

Electronic Inks and Pastes

Silver Conductive Composition

Micromax™ LL500 is a gold via fill compatible with the Micromax™ GreenTape™ 9K7 low temperature co-fired ceramic (LTCC) tape material and the gold system's companion co-fired conductor members: Micromax™ LL505 (internal), Micromax™ LL507 (external) and Micromax™ LL509 (solderable). Micromax™ LL500 is cadmium and lead free*.

Product benefits

When used as the via fill in the Micromax™ GreenTape™ 9K7 LTCC system, Micromax™ LL500 offers the following benefits:

- High reliability, high conductivity metallization
- Co-fire processing
- High circuit density
- Cadmium and lead free*

*Cadmium and lead 'free' as used herein means that cadmium and lead are not intentional ingredients in and are not intentionally added to the referenced product. Trace amounts however may be present.

Product information

Solvent or thinner	Micromax™ 9450
Solid content	94 - 96 ^[1] %
[1]: 750 °C	

Rheological properties

Viscosity	7500 - 9500 ^[2] Pa.s
[2]: Brookfield HBT, UC&SP, SC4-14/6R, 1 rpm, 25 °C	

Application technique

Drying time	5 min
Drying temperature	100 °C
Via, diameter resolution	100 µm

Electrical properties

Surface resistivity	≤5 ^[3] mOhm per square
---------------------	-----------------------------------

[3]: normalized to 15µm dry thickness

Micromax™ LL500

Electronic Inks and Pastes

Storage and stability

Shelf life

3^[4] months

[4]: in unopened containers, from date of shipment, at temperature <25 °C

Additional information

How to use

Processing features

- For detailed recommendations on the use of the Micromax™ LL500 via fill with the Micromax™ GreenTape™ 9K7 system, consult this data sheet and the Micromax™ GreenTape™ LTCC Design Guide. For compatible co-fired and post fired conductor compositions, consult the Micromax™ GreenTape™ 9K7 Product Selector Guide.

Processing

• Printing

- The composition should be thoroughly stirred prior to use. This is best achieved by a slow, gentle mixing by hand for 1 to 2 minutes using a clean, burr-free spatula (flexible plastic or stainless steel). Care must be taken to avoid air entrapment.
- Prior to the via fill step, via openings are formed/punched in the preconditioned Micromax™ GreenTape™ 9K7 green sheets per the applicable circuit design for the respective layers.
- Print Micromax™ LL500 directly into the open vias using typical through-hole screen printing methods and a stencil mask. The use of a vacuum stone or other support structure which uniformly distributes a vacuum across the green sheet is recommended to assist with the uniform and complete filling of the via array patterns, as well as secure the green sheet to the printer's stage plate during the printing process.
- Printing should be performed in a clean, well-ventilated area. Optimum printing characteristics are generally achieved when the room and paste container temperatures are in the 20 to 23 °C range.

• Clean-up solvent

- 1-Propoxy-2-Propanol

• Drying

- Dry via prints in a well ventilated oven or conveyor dryer for 5 minutes at 100 °C. Do not over-dry. An alternative drying method is to allow the Micromax™ LL500 fills to dry 6 to 8 hours at ambient room temperature.

• Lamination

- Collate, stack and laminate multiple sheets of the printed circuit

Micromax™ LL500

Electronic Inks and Pastes

patterns according to the recommended processing parameters detailed in the Micromax™ GreenTape™ LTCC Design Guide.

- Typical lamination parameters are 3000 psi at 70°C for 10 minutes. Lamination pressures may vary slightly based upon part design and the individual tape lot shrinkage factors.

• Firing

- Fire in a well ventilated conveyor or static furnace. Air flows and extraction rates should be optimized to ensure that oxidizing conditions exist within the muffle and that no exhaust gases enter the room.
- Micromax™ GreenTape™ 9K7 requires the use of dedicated, specially coated setters in order to prevent parts from sticking during firing.
- Consult the Micromax™ GreenTape™ 9K7 low temperature co-fired ceramic (LTCC) system data sheets and Micromax™ GreenTape™ LTCC Design Guide for additional details.
- For further information regarding firing profiles, furnace recommendations and setter tile choices, please contact your local Micromax™ Technical Service Representative.

Properties

- Information in this datasheet shows anticipated typical physical and electrical properties for Micromax™ LL500 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

Storage and shelf life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25°C). Shelf life of material in unopened containers is three months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Safety and handling

For safety and handling information pertaining to this product, read Safety Data Sheet (SDS).

Micromax™ LL500

Electronic Inks and Pastes

Printed: 2023-09-21

Page: 4 of 4

Revised: 2023-06-21 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2023 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC. KEPITAL is a registered trademark of Korea Engineering Plastics Company, Ltd.