

Micromax™ ME801

Electronic Inks and Pastes

Transparent Conductor

Micromax™ ME801 is part of the Micromax™ suite of materials developed for In Mold Electronic applications. Micromax™ ME801 is a transparent conductive ink capable of withstanding thermoforming and overmolding temperatures. This composition is intended to be used for Capacitive Switch applications.

Product benefits

- Highly transparent
- High light transmission
- Excellent stability at 85 °C/85% RH
- Very good white light/LED stability

Product information

Colour	Blue
Solid content	2.5 - 5.5 ^[1] %
[1]: 150 °C	

Rheological properties

Viscosity	8 - 40 ^[2] Pa.s
[2]: Brookfield DVII-Pro Cone plate at shear force 0.2/sec	

Application technique

Mask mesh	280 ^[3]
Drying time	5 ^[4] min
Drying temperature	120 ^[4] °C
Recommended film thickness, dried	1 ^[5] µm
[3]: Screen Types: Stainless steel	
[4]: box oven	
[5]: 280 mesh stainless steel	

Electrical properties

Surface resistivity	≤500000 mOhm per square
---------------------	-------------------------

Micromax™ ME801

Electronic Inks and Pastes

Storage and stability

Shelf life

6^[6] months

[6]: in unopened containers, from date of shipment, at temperature <25°C

Additional information

How to use

Processing

- **Substrates**
 - Polycarbonate, surface-treated polyester
- **Screen types**
 - Polyester, stainless steel
- **Printing**
 - Reel-to-reel, semi-automatic or manual
 - Polyester or steel mesh can be used. A water and solvent resistant emulsion is recommended.
 - If gelatinous particulate phase is present, gentle stirring and avoiding air entrapment will return the ink to a homogeneous state. Best print results are obtained with minimal squeegee pressure, a higher print speed and with a print/flood mode on the printer setting.
- **Typical circuit line thickness**
 - 1 µm
 - Printed with SD 56/36 (280mesh) stainless steel or 77-48 PET Screen
- **Work life**
 - > 1 hour
- **Clean-up solvent**
 - Ethylene glycol diacetate
- **Drying**
 - Box oven : 120°C for 5 minutes
 - Reel-to-reel : 120°C for 3 minutes
 - Dry in a well-ventilated box oven or belt/conveyor furnace. Air flow and extraction rates should be optimized to ensure complete removal of solvent from the paste. A strong air flow may help to reduce the drying temperature combination. It will also aid in achieving the lowest as-printed resistance.

Properties

Typical Physical Properties

Test	Properties
SER OD	< 15

Micromax™ ME801

Electronic Inks and Pastes

%VLT	≥ 90
Low Haze	< 0.3% after 1000hrs at 85/85% humidity

Information in this datasheet shows anticipated typical physical properties for Micromax™ ME801 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

Storage and shelf life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25 °C). Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Safety and handling

For safety and handling information pertaining to this product, read Safety Data Sheet (SDS).

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2023 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC. KEPITAL is a registered trademark of Korea Engineering Plastics Company, Ltd.