
ATEVA® 4200ACG - EVA

Description

This resin is commonly used for medical and dental applications and is manufactured to comply with USP Class VI.

Physical properties	Value	Unit	Test Standard
Melt flow index, MFI	82	g/10min	ASTM D1238
Temperature	190	°C	ASTM D1238
Load	2.16	kg	ASTM D1238
Vinyl Acetate	41	%	Internal

Characteristics

Regulatory Medical grade

Additives Antioxidant