

Micromax™ 1749R

Microcircuit and Component Materials

Series 17 Resistors

High Reliability Hybrid Microcircuits And Precision Resistor Network 10Ω - 1MΩ/sq Silver Alloy Terminations

Micromax™ Series 1700 Resistor Compositions have been developed as part of a materials system for use in the manufacture of high reliability hybrid circuits requiring high stability, low TCR, and low process sensitivity.

Product benefits

- Post laser trim stability of less than 0.5% average ΔR under all standard testing conditions.
- TCRs of less than 100 ppm/°C, even with blends.
- Low sensitivity to variations in firing temperature, time at peak and resistor geometry.

Product information

Solvent or thinner
Blend member or series

[1]: Blend Member B

Micromax™ 4036
17 Resistors Series ^[1]

Rheological properties

Viscosity

145 - 210^[2] Pa.s

[2]: HAT UC & #14 Spindle, 10rpm, 25°C±1°C

Application technique

Mask mesh

200^[3]

Mask emulsion

12 - 18 μm

Drying time

10 - 15 min

Drying temperature

150 °C

Theoretical coverage

80 - 110 cm²/g

Recommended film thickness, dried

22 - 28 μm

Leveling time

5 - 10 min

[3]: stainless steel

Electrical properties

Surface resistivity

9E7 - 1.1E8^[4] mOhm per square

Hot Temperature Coefficient Resistance

-100 - 100^[5] ppm/K

Cold Temperature Coefficient Resistance

-100 - 100^[6] ppm/K

Noise

2^[7] dB

Short Term Overload Voltage

≥280 V/mm

Standard Working Voltage

110^[9] V/mm

Micromax™ 1749R

Microcircuit and Component Materials

Maximum Rated Power Dissipation $120^{[10]}$ m/(W.mm²)
 Voltage Coefficient of Resistance $-40^{[11]}$ ppm

[4]: Typical resistor properties based on laboratory tests using recommended processing conditions: terminations : Micromax™ Palladium/Silver Conductor Composition 9308 prefired at 850 °C; substrate : 96% alumina; printing : 200-mesh stainless steel screen (18 µm emulsion thickness) to a dried thickness of 25±3 µm; firing : 60-min cycle to peak temperature of 850 °C for 10 minutes. Shipping specifications. Resistor geometry : 1.5 mm x 1.5 mm.

[5]: Temperature Coefficient of Resistance +25+125 °C

[6]: Temperature Coefficient of Resistance -55+25 °C

[7]: Resistor geometry : 1 mm x 1 mm, Firing cycle, 60 minute cycle to peak temperature of 850 °C for 10 minutes.

[8]: Short Term Overload Voltage : required (5 second duration) to induce a resistance change of 0.25% in a 1 mm x 1 mm resistor at 25 °C.

[9]: Standard working voltage : 0.4 x Short Term Overload Voltage.

[10]: Maximum Rated Power Dissipation : (Standard Working Voltage)²/Resistance

[11]: ppm/V/mm, Resistor geometry 1 mm x 1 mm laser trimmed with P-cut to 1.5x average fired value. VCR measured from 5-50 VDC.

Storage and stability

Shelf life $6^{[12]}$ months

[12]: in unopened containers, from date of shipment, at temperature <25° C

Additional information

How to use

Processing

• Termination

- Unless otherwise stated, reported properties are based on tests with Micromax™ 9308 silver/palladium conductor composition, prefired at 850 °C. Excellent results have also been obtained using other silver/palladium conductor compositions. The precious metal alloy compositions are prefired at 850 °C.

• Substrates

- Reported properties are based on tests on 96% alumina substrates. Substrates of other compositions and from various manufactures may result in variations in performance properties.

• Resistor geometry

- Micromax™ Series 1700 compositions are Quality Assurance tested using a 1.5 mm x 1.5 mm resistor with prefired silver/palladium Micromax™ 9308 terminations. Variations in resistor geometry will result in slight variations in resistivity and TCR.

• Printing

- Specified properties are based on resistors printed to 25±3 µm dried print thickness. This is readily achieved using 200-mesh stainless steel screens with 15±3 µm emulsion thickness. Nylon or polyester screens may be used in some applications although a lower mesh count of 150-175 will usually be required to achieve equivalent print thickness.

Micromax™ 1749R

Microcircuit and Component Materials

- **Drying**
 - Prints should be allowed to level at room temperature and then dried.
- **Effect of variations in thickness**
 - Print thickness outside the 20-30 µm range may result in compromised TCR and/or stability characteristics.
- **Firing**
 - Micromax™ Series 1700 resistivity and TCR specifications are based on a 60-min firing cycle with a 10-min peak at 850 °C, 20 min above 800 °C and 30 min above 600 °C.
- **Refire sensitivity**
 - 10kΩ/sq or lower resistors change very slightly on refiring. The 100k and 1MΩ/sq resistors show significant increases in resistivity on refiring; however, TCR's remain well within the ±100 ppm/°C limits.
- **Encapsulant**
 - In general, glass encapsulation is not required. However, in applications which require mechanical protection or protection from extreme environments such as high temperature nitrogen or forming gas, Micromax™ QQ550 encapsulant fired at 500 °C is recommended. Glass encapsulation of 1 mm x 1 mm resistors terminated with silver/palladium Micromax™ 9308 shifts the resistivity of Micromax™ Series 1700 resistors by less than 1%.

Properties

- Information in this datasheet shows anticipated typical physical properties for Micromax™ 1700 series based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

Storage and shelf life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25 °C). Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Safety and handling

For safety and handling information pertaining to this product, read Safety Data Sheet (SDS).

Micromax™ 1749R

Microcircuit and Component Materials

Printed: 2023-03-30

Page: 4 of 4

Revised: 2023-03-26 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2023 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC. KEPITAL is a registered trademark of Korea Engineering Plastics Company, Ltd.