

Micromax™ 5742

Microcircuit and Component Materials

Gold-Cofireable Conductor

Micromax™ 5742 is intended for use as a co-fired gold conductor for Micromax™ GreenTape™ 951 System. Micromax™ 5742 can be used as an internal or external conductor for all gold systems or as an external conductor on traditional mixed metal systems. Micromax™ 5742 is wire bondable with 1 mil Au and 1 mil Al wire.

Product benefits

When used with GreenTape™ 951 compatible via fill pastes, Micromax™ 5742 offers the following benefits:

- High reliability
- High conductivity
- High circuit density
- Au and Al wire bondable (1 mil)

Product information

Solvent or thinner

Solid content

[1]: 750°C

Micromax™ 8250

79.5 - 81.5^[1] %

Rheological properties

Viscosity

100 - 180^[2] Pa.s

[2]: Brookfield HAT #14 Spindle; 10 RPM @ 25°C

Application technique

Mask mesh

325^[3]

Mask emulsion

12 µm

Drying time

5 - 10 min

Drying temperature

80 - 120 °C

Theoretical coverage

80 - 90^[4] cm²/g

Recommended film thickness, dried

13 - 18 µm

Recommended film thickness, fired

6 - 12 µm

Print resolution, lines

125^[5] µm

Print resolution, spaces

125^[5] µm

Leveling time

5 - 10 min

[3]: Screen Types: Stainless steel

[4]: Calculated at a wet thickness of 25µm

[5]: Dried Line Resolution

Micromax™ 5742

Microcircuit and Component Materials

Electrical properties

Surface resistivity

$\leq 5^{[6]}$ mOhm per square

[6]: @9µm fired thickness

Storage and stability

Shelf life

6^[7] months

[7]: in unopened containers, from date of shipment, at room temperature (<25°C)

Additional information

How to use

Design & compatibility

- Design compatibility

- Micromax™ has tested this composition with the GreenTape™ 951 System. It is impractical to cover every combination of materials, customer processing conditions and circuit layout. It is therefore essential that customers thoroughly evaluate the material in specific situations to completely satisfy themselves with the overall quality and suitability of the composition for its intended application(s).

Processing

- Substrates

- Micromax™ GreenTape™ 951

- Printing

- The composition should be thoroughly mixed prior to use. This is best achieved by slow, gentle, hand- stirring with a clean, burr-free, flexible plastic spatula for 1 – 2 minutes. Care must be taken to avoid air entrapment.
- Printing should be performed in a clean, well- ventilated area. Optimum printing characteristics are generally achieved in the room temperature range of 20 – 23°C. It is therefore important that the material, in its container, is at this temperature prior to printing.
- Print Micromax™ 5742 directly onto un-fired GreenTape™ 951 using thick film printing methods and a vacuum stone or other support structure that uniformly distributes vacuum.

- Thinning

- This composition is optimized for screen printing; however, thinning may be required periodically to replenish solvent loss due to evaporation. Use the Micromax™ recommended thinner

Micromax™ 5742

Microcircuit and Component Materials

Micromax™ 8250 for slight adjustments to viscosity. The use of too much thinner or the use of non-recommended thinner may affect the rheological behavior of the material and its printing characteristics.

- **Clean-up solvent**
 - 1-Proxy-2- Propanol
- **Drying**
 - Allow prints to level at room temperature and then dry in a well-ventilated oven or conveyor dryer. Typical drying conditions can range between 80 – 120°C for 5 – 10 minutes.
 - Do not over dry.
- **Lamination**
 - Laminate external tape layers printed with multiple sheets of GreenTape™ using the recommended processing parameters outlined in the GreenTape™ Design Guideline and the GreenTape™ 951 product data sheets. Typical lamination conditions are 3000 psi at 70°C for 10 minutes.
- **Firing**
 - Consult the GreenTape™ 951 technical data sheets for firing recommendations. Fire in a well-ventilated conveyor or static furnace with optimized air flows and extraction rates to ensure oxidizing conditions within the firing zone. Contact your Micromax™ technical representative for details.

Properties

Typical Physical and Electrical Properties

Test	Properties
Dried Line Resolution (μm) [lines/spaces]	125/125
Wirebond 1 mil Au, Initial (g)	>9
Wirebond 1 mil Au, Aged* ³ 1000h (g)	>9
Wirebond 1 mil Al, Initial (g)	>9
Wirebond 1 mil Al, Aged* ³ 1000h (g)	>8

*³ Aged at 150°C

Information in this datasheet shows anticipated typical physical properties for Micromax™ 5742 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

Micromax™ 5742

Microcircuit and Component Materials

Storage and shelf life

Container should be stored, tightly sealed, in a clean, stable environment at room temperature (<25 °C). Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Safety and handling

For safety and handling information pertaining to this product, read Safety Data Sheet (SDS).

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2023 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC. KEPITAL is a registered trademark of Korea Engineering Plastics Company, Ltd.