

Micromax™ 7102

Microcircuit and Component Materials

Carbon Conductive Composition

Micromax™ 7102 carbon is used as conductor in designs that tolerate high resistivity. Major benefits include low cost and excellent screen life and high-temp stability. It can be used with semi- automatic and manual printers. Micromax™ 7102 may be blended with these Micromax™ compositions to meet specific resistance requirements: Micromax™ 7082 Carbon, DoPont 5028 Ag and Micromax™ 3571 Dielectric.

Product benefits

- Low resistivity carbon
- High stability
- Superior activity in biomedical applications
- Excellent adhesion to polycarbonate substrates
- Lead, Cadmium, Nickel and Phthalate free*

* Lead, Cadmium, Nickel and Phthalate 'free' as used herein means that lead, cadmium, nickel and phthalate are not intentional ingredients in and are not intentionally added to the referenced product. Trace amount however may be present.

Product information

Solvent or thinner	Micromax™ 3610
Solid content	34.5 - 37.5 ^[1] %
[1]: 150°C	

Rheological properties

Viscosity	60 - 125 ^[2] Pa.s
[2]: Brookfield RVT, 10 rpm, #14 spindle & UC, 25°C	

Application technique

Mask mesh	200
Drying time	5 - 6 ^[3] min
Drying temperature	120 ^[3] °C
Theoretical coverage	103 cm ² /g
Recommended film thickness, dried	9 - 15 µm
[3]: Box Oven	

Storage and stability

Shelf life	6 ^[4] months
[4]: in unopened containers, from date of shipment, at temperature <25°C	

Micromax™ 7102

Microcircuit and Component Materials

Additional information

How to use

Processing

- **Screen types**
 - Stainless steel, Polyester
- **Printing**
 - Semiautomatic, manual
- **Typical circuit line thickness**
 - Printed with 200-mesh stainless steel screen
 - 9 - 15 μm
- **Worklife**
 - > 2 hours
- **Clean-up solvent**
 - Ethylene diacetate or methyl propasol acetate

Properties

Typical Physical Properties on 5-mil Polyester Film

Test	Properties
Abrasion Resistance, Pencil Hardness (ASTM D3363-74) [H]	2
Resistivity after Flex (Ω/sq) at 25.4 μm 15 sec after test Crease (180°, 1 cycle)	50

Information in this datasheet shows anticipated typical physical properties for Micromax™ 7102 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

Storage and shelf life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25°C). Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Safety and handling

For safety and handling information pertaining to this product, read Safety Data

Micromax™ 7102

Microcircuit and Component Materials

Sheet (SDS).

Printed: 2023-03-30

Page: 3 of 3

Revised: 2023-03-17 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2023 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC. KEPITAL is a registered trademark of Korea Engineering Plastics Company, Ltd.