

Micromax™ 9318

Microcircuit and Component Materials

Resistors Composition

Micromax™ 9318 is low-resistivity, particularly suited to potentiometer and trimmer uses. The contact resistance variation of these compositions is excellent and they offer predictable, reproducible resistance values.

Product information

Solvent or thinner

Micromax™ 8250

Rheological properties

Viscosity

185 - 270^[1] Pa.s

[1]: Brookfield HBT, SC4-14/6R, 10 rpm, 25 °C

Application technique

Mask mesh

165 - 200

Mask emulsion

17.8 µm

Drying time

10 - 15 min

Drying temperature

100 - 150 °C

Theoretical coverage

65 - 85^[2] cm²/g

Recommended film thickness, dried

22 - 28 µm

Leveling time

5 - 15 min

[2]: at 50µm wet film thickness

Electrical properties

Surface resistivity

1350 - 1650 mOhm per square

Hot Temperature Coefficient Resistance

-250 - 250^[3] ppm/K

Cold Temperature Coefficient Resistance

-250 - 250^[4] ppm/K

[3]: from +25 to +125 °C for Hot TCR

[4]: from -55 to +25 °C for Cold TCR

Storage and stability

Shelf life

6^[5] months

[5]: in unopened containers, from date of shipment, at temperature <25° C

Additional information

How to use

Processing

• Termination compatibility

- Micromax™ 9318 resistor composition is compatible with Micromax™ Palladium/Gold 8651. Other conductors have not

Micromax™ 9318

Microcircuit and Component Materials

as yet been tested for compatibility.

- **Printing**

- Micromax™ 9318 resistor compositions are formulated for screen printing with 165-200 mesh woven wire of filament screens. 200-mesh stainless steel screens with 0.7mil emulsion thickness normally product the recommended 25µm dried thickness necessary to obtain the stated performance characteristics. Satisfactory results can be obtained with dried thickness of 22-28µm. Variations in print thickness will result in corresponding variations in performance characteristics, particularly sheet resistivity. Control and reproducibility of print thickness is essential to obtain predictable, reproducible fired resistor properties.

- **Drying**

- Prints should be dried 5-15 minutes at room temperature to permit leveling of screen mesh marks. Drying may then be completed in 10-15 minutes at 100-150 °C.

- **Firing**

- Micromax™ 9318 resistor compositions should be fired in a belt furnace using the standard Micromax™ firing profile. A peak firing temperature of 850 °C (10 minutes at peak) with a total cycle of 60 minutes is recommended.

- **Encapsulant**

- Micromax™ 9318 resistor compositions are not encapsulated when used in trimmers.

Properties

Fired Resistor Properties

Test	Properties
Contact Resistance Variation (CRV) (%)	~1.00

All values reported here are results of experiments in our laboratories intended to illustrate product performance potential with a given experimental design. They are not intended to represent the product's specifications.

Storage and shelf life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25 °C). Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Micromax™ 9318

Microcircuit and Component Materials

Safety and handling

For safety and handling information pertaining to this product, read Safety Data Sheet (SDS).

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2023 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC. KEPITAL is a registered trademark of Korea Engineering Plastics Company, Ltd.